

WHT-6430

Description WHT-6430 is polyester-based TPU hot-melt adhesive, supplied in form of white or slightly yellowish pellets with the characteristic of high viscosity, fast crystallization rate, and good adhesion strength to PVC, PU, fabric and genuine leather.

Application Solution adhesive for footwear, fabric coatings, hot-melt adhesive film and tape.

Working instructions WHT-6430 is generally used in MEK, EAc, TOL, Acetone solutions with 15% solid content. While WHT-6430 is used as hot-melt, the characteristics of the extruder are the followings:

- L/D ratio between 25:1 and 30:1 for extrusion.
- The extruder screw must have 3 zones and a compression ratio between 2:1 and 3:1. Screws with a compression ratio greater than 4:1 should be avoided.
- The extruder screw should have a continuous regulation device and a working power higher than for processing other plastics.

For optimum results, previous drying of the product during 3-6 hours at 40~50°C is advisable, in a hot air circulatory, vacuum or desiccant-air dryer. The suggested processing-temperature profiles for injection are depicted in the table below.

Property

PROPERTY	Method	Units	6430
Hardness	ASTM D 2240	Shore A	97
Density	ASTM D 792	g/cm ³	1.2
Tensile strength	ASTM D 412	MPa	44
Ultimate elongation	ASTM D 412	%	650
Solution viscosity (15% in MEK, 23 °C)	ISO 3219	mPa.s	2600~3600
Suggested Activation temperature		°C	70~110

These products can only be ordered in typical quantities.

Please contact your sales representative for details.

T-die Extrusion Guideline for WHT-6430

Product	Die (°C)	Metering (°C)	Compression(°C)	Feed (°C)	Drying temperature(°C)	Drying time (h)
6430	180	180	170	150	40-50	3-6

Note: The actual processing temperature should be adjusted properly while auxiliary materials were used.

Regrind usage

Where end-use requirements permit, up to 20% resin regrind may be used with virgin material, provided that the material is kept free of contamination and is properly dried (see section on Drying). Any regrind used must be generated from properly molded/extruded parts, sprues, runners, trimmings, and/or films. All regrind used must be clean, uncontaminated, and thoroughly blended with virgin resin prior to drying and processing. Under no circumstances should degraded, discolored, or contaminated material be used for regrind. Materials of this type should be discarded. Improperly mixed and/or dried regrind may diminish the desired properties. It is critical that you test finished parts produced with any amount of regrind to ensure that your end-use performance requirements are fully met.

Disclaimer

The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products



Yantai Wanhua Polyurethanes Co., Ltd

Add: No.7 South Xingfu Road, Yantai, Shandong 264002, P. R. China

Tel: +86-535-338-8825 Fax: +86-535-685-7160

Website: www.wanthane.com E-mail: tpuservice@ytpu.com

Edition 2011

Page 1 / 1